



# Silvercoat Bright Galvanizing Spray

**Bright-Aluminum Finish with High Zinc Content: Formulated for touch-up and repair of Hot Dip Galvanized**



12oz net wt can

**Silvercoat Bright Galvanizing Spray** is a fast drying zinc compound spray that protects steel and ferrous metals exposed to severe corrosive environments. **It provides the long-lasting protection of zinc, yet closely matches the bright color of Hot Dip Galvanizing.** This high performance epoxy compound fuses zinc to the metal substrate and protects against corrosion. **Silvercoat Bright Galvanizing Spray** contains 70% zinc in the dry film. It meets ASTM A780 specifications and is widely used for recoating and touching-up damaged galvanized surfaces.

**Silvercoat Bright Galvanizing Spray** is self-healing, and prevents creepage even when the surface is penetrated or scratched. After curing, it may be coated with conventional primers and finishes such as epoxy, urethanes, acrylics & chlorinated rubber.

### Surfaces Include

<ul style="list-style-type: none"> <li>• Structural Steel</li> <li>• Wrought Iron</li> <li>• Welds</li> <li>• Bridges</li> </ul>	<ul style="list-style-type: none"> <li>• Fences</li> <li>• Gutters</li> <li>• Food Plants</li> <li>• Power Plants</li> </ul>	<ul style="list-style-type: none"> <li>• Towers</li> <li>• Damaged Surfaces</li> <li>• Automotive Panels</li> <li>• Refineries</li> </ul>
--	--	---

### Features

- 70% Organic zinc content in dry film
- Bright Silver Appearance
- Self-healing; protects even when surface is dented or scratched

### Mil-Specifications

P-26915A	- Primer for Steel (USAF)
P-21035	- Repair of Hot Dip Galvanizing
P-46105	- Weld through Primer
ASTM A239	- Comparable to Hot Dip Galvanizing
ASTM A780	- Repair of Hot Dip Galvanizing

### Surface Preparation

**New Steel:** Surface must be dry and free of contamination. Remove all weld splatter and grind all rough welds and sharp edges to a smooth contour. For severe exposure (immersion, chemical etc) near-white blast clean.

**Previously Painted Surfaces:** Must be free of oil, grease or other contamination. For best results, spot blast exposed areas to be primed. Power tool brushings may be used for minor touch-up.

### Spraying

Shake can for 30 seconds after agitator ball begins to rattle. Spray dry-prepared surface in even passes until completely covered and wet. Apply a second coat after 10 to 15 minutes for additional protection. Double lap all welds, seams, corners & edges to ensure film thickness. Coating will dry to the touch within 15 minutes and will cure overnight. Baking for 10 minutes at 300 degrees F will speed curing.

### CAUTION

CONTENTS ARE EXTREMELY FLAMMABLE AND UNDER PRESSURE. Store below 120°F, away from heat sources and out of direct sunlight. Do not puncture or incinerate (burn). Use in well ventilated areas. Harmful or fatal if swallowed. Never use direct heat to warm aerosol cans! Only warm water. Read Material Safety Data Sheet for more hazardous information.

### Specifications

Appearance	Bright Silver Zinc
Can Size	16 oz. can size
Net Wt.	12 oz. net wt. (340g)
Coverage per Can	1 mil = 18 Sq. Ft. 2-1/2 mil = 7.5 Sq. Ft.
Zinc Content	70% in Dry Film
Drying Time	5- Minutes to Touch 12- Hours to Total Cure
Temperature Resistance	400°F – Sustained 600°F – Intermittent

### Packaging

1-case (12 x 12oz net wt cans)

F.O.B. Phila, PA U.S.A.

### For More Info, Contact:

#### Clearco Products Co., Inc.

15 York Road  
Willow Grove, PA 19090  
U.S.A.

Tel: (215) 366-7860

Fax: (215) 366-7862

Email: [info@clearcoproducts.com](mailto:info@clearcoproducts.com)

Web: [www.clearcoproducts.com](http://www.clearcoproducts.com)



# Product Information

## High Performance Zinc Spray

Formulated with 90% + Zinc...meets and exceeds ASTM A780 specifications for touch-up and repair of Hot Dip Galvanize



**High Performance Zinc Spray** is a fast drying zinc compound spray that protects steel and ferrous metals exposed to severe corrosive environments. It is formulated for heavy maintenance, and is used on exterior surfaces subjected to severe corrosion & rust conditions. This high performance epoxy compound fuses zinc to the metal substrate and protects against corrosion equal to Hot Dip Galvanizing.

The finished film of HP Zinc Spray contains > 90% Zinc in the dry film. It protects the surface, even when penetrated or scratched, as an insoluble Zinc Oxide coating that forms over the exposed area. High Performance Zinc Spray meets and exceeds ASTM A780 specifications, and is widely used for recoating and touching-up damaged galvanized surfaces.

After curing, the HP Zinc film may be coated with conventional primers and finishes such as epoxy, urethanes, acrylics & chlorinated rubber. High Performance Zinc Spray is highly Resistant to salt corrosion & water.

### Surfaces Include

- Structural Steel
- Wrought Iron
- Welds
- Bridges
- Fences
- Automotive Panels
- Damaged Galvanized Surfaces
- Gutters
- Food Plants
- Refineries
- Off shore rigs

### Features:

- 90% Organic Zinc in Dry Film
- Long Term Corrosion Protection
- Meets ASTM A780 Specifications
- Provides the equivalent protection of Hot Dip Galvanize to damaged Galvanized surfaces.  
Self-healing: provides protection even when scratched.

### Mil & ASTM Specs

P-26915A.....Primer for Steel (USAF)
P-21035.....Repair of Hot Dip Galvanizing
P-46105.....Weld through Primer
ASTM A239.....Comparable to Hot Dip Galvanizing
ASTM D-1748..... will pass 1,000 + hours in the 5% Salt Spray Booth
ASTM-A 780-80.....minimum of 92% zinc by weight.

### Specifications

Appearance	Gray
Can Size	16 fl. oz.
Net Weight	14 oz. net wt.
Packing	12 x 14 oz. net wt. cans per case
Coverage per Can	1 Mil = 25 Sq. Ft. 2-1/2 Mil = 10 Sq. Ft.
Zinc Content	90+% in Dry Film
Drying Time	5-Minutes to Touch 12-Hours to Total Cure
Temperature Resistance	400°F – Sustained 600°F – Intermittent

### Contains

Zinc Dust (CAS #7440-66-6), Toluene (CAS #108-88-3), Isobutane (CAS #75-28-5), Propane (CAS #74-98-6) & Naptha (CAS #8030-30-6)
---

### Packaging

1-case (12 x 14oz net wt)
F.O.B. Phila, PA U.S.A.

### SURFACE PREPARATION:

*New Steel: Surface must be dry and free of contamination. Remove all weld splatter and grind all rough welds and sharp edges to a smooth contour. For severe exposure (immersion, chemical etc) near-white blast clean.*

*Previously Painted Surfaces: Must be free of oil, grease or other contamination. For best results, spot blast exposed areas to be primed. Power tool brushings may be used for minor touch-up.*

### SPRAYING:

*Shake can for 30-seconds after agitator ball begins to rattle. Spray dry-prepared surface in even passes until completely covered and wet. Apply a second coat after 10 to 15-minutes for additional protection. Double lap all welds, seams, corners & edges to ensure film thickness. Coating will dry to the touch within 15 minutes and will cure overnight. Baking for 10*

### For More Info, Contact:

#### Clearco Products Co., Inc.

15 York Road  
Willow Grove, PA 19090  
U.S.A.

Tel: (215) 366-7860

Fax: (215) 366-7862

Email: [info@clearcoproducts.com](mailto:info@clearcoproducts.com)

Web: [www.clearcoproducts.com](http://www.clearcoproducts.com)